

E-Glass

Raw Material Used

E-Glass yarns and threads, textured E-Glass yarns,
Diameter specified 9 - 13 μm

Application temperature

450°C, Short term up to 550°C

Properties:

- no health risks as free of asbestos and ceramic fibers
- fire-proof
- non-ageing
- good electrical insulation
- good thermal insulation
- oil and solvent resistant - chemical resistance (pH 3-9)
- not hygroscopic
- environmentally friendly



Textilglas-Technologie

GmbH & Co. KG

Max-Planck-Strasse 15-19

DE-49593 Bersenbrück

Phone: +49 (0) 5439 / 94 16-0

Fax: +49 (0) 5439 / 94 16-10

Email: info@culimeta.de

Internet: www.culimeta.de

